

Product Data Sheet

Thioplast™ G10

Status:
 December 2018

Liquid polysulfide polymer with thiol end groups

Description	Liquid Polysulfide Pre-polymer, end-capped by SH-functional end groups.																						
Properties¹⁾ <small>1) Typical properties, not to be construed as product specifications</small>	<table> <tr> <td>Appearance</td> <td>brownish liquid polymer</td> </tr> <tr> <td>SH content</td> <td>1,4 – 1,5% (related to viscosity/Molecular weight)</td> </tr> <tr> <td>Viscosity (25 °C)</td> <td>42 – 48 Pas</td> </tr> <tr> <td>Av. Molecular weight</td> <td>4400 – 4700 g/mol (relative to SEC standard)</td> </tr> <tr> <td>Branching</td> <td>0,0 mol% (calculated on mol% TCP)</td> </tr> <tr> <td>Water content</td> <td>max. 0,35%</td> </tr> <tr> <td>Free sulfur</td> <td>0.01 – 0.1%</td> </tr> <tr> <td>Volatiles</td> <td>max. 0.5%</td> </tr> <tr> <td>Glass point</td> <td>approx. – 55 °C</td> </tr> <tr> <td>Flash point</td> <td>> 230 °C</td> </tr> <tr> <td>CAS-No</td> <td>68611-50-7</td> </tr> </table>	Appearance	brownish liquid polymer	SH content	1,4 – 1,5% (related to viscosity/Molecular weight)	Viscosity (25 °C)	42 – 48 Pas	Av. Molecular weight	4400 – 4700 g/mol (relative to SEC standard)	Branching	0,0 mol% (calculated on mol% TCP)	Water content	max. 0,35%	Free sulfur	0.01 – 0.1%	Volatiles	max. 0.5%	Glass point	approx. – 55 °C	Flash point	> 230 °C	CAS-No	68611-50-7
Appearance	brownish liquid polymer																						
SH content	1,4 – 1,5% (related to viscosity/Molecular weight)																						
Viscosity (25 °C)	42 – 48 Pas																						
Av. Molecular weight	4400 – 4700 g/mol (relative to SEC standard)																						
Branching	0,0 mol% (calculated on mol% TCP)																						
Water content	max. 0,35%																						
Free sulfur	0.01 – 0.1%																						
Volatiles	max. 0.5%																						
Glass point	approx. – 55 °C																						
Flash point	> 230 °C																						
CAS-No	68611-50-7																						
Application	<p>Thioplast G10 is used to formulate highly flexible and elastic sealants being used in aerospace applications with best performance in Jet Fuel resistance, high Nobel Gas retention and low moisture vapor permeability.</p> <p>Furthermore, Thioplast G10 is used in sealants with high elasticity and good UV-resistance being used in construction applications.</p>																						
Curing	<p>Curing agent: Manganese(IV)-oxide (*): 5,7 – 6,3 g/100 g Thioplast G 10 (*) Pure curing agent: Manganese (IV)-oxide. The concentration of active/activated Manganese (IV)-oxide needs to be considered.</p> <table> <tr> <td>Curing paste</td> <td>pbw</td> </tr> <tr> <td>MnO₂, Grade Honeywell FA</td> <td>100</td> </tr> <tr> <td>Santicizer 278</td> <td>100</td> </tr> <tr> <td>Perkacit DPG</td> <td>6</td> </tr> <tr> <td>Airex 900</td> <td>7.4</td> </tr> </table> <p>Properties of Thioplast G10 cured with 15 g curing paste/100 g Thioplast G10:</p> <table> <tr> <td>Shore A-hardness</td> <td>min 20</td> </tr> <tr> <td>Elongation @ break %</td> <td>min 300</td> </tr> </table>	Curing paste	pbw	MnO ₂ , Grade Honeywell FA	100	Santicizer 278	100	Perkacit DPG	6	Airex 900	7.4	Shore A-hardness	min 20	Elongation @ break %	min 300								
Curing paste	pbw																						
MnO ₂ , Grade Honeywell FA	100																						
Santicizer 278	100																						
Perkacit DPG	6																						
Airex 900	7.4																						
Shore A-hardness	min 20																						
Elongation @ break %	min 300																						
Packaging	Thioplast G10 is available in 200 Liter drums, 1000 Liter IBC and 20m ³ ISO Bulk.																						
Storage	Store the container in cool and dry area, keep it closed when not in use. Shelf life under appropriate storage conditions min 3 years.																						
Handling	Full information on the safe handling is available in the Material Safety Data Sheet (MSDS). Further details are available upon request.																						

Legal Disclaimer: All information is based upon tests and data believed to be reliable, however, it is the user's responsibility to determine the suitability for his own use of the products described here. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent. All orders accepted shall be subjected to the standard conditions of sale of the manufacturing company, Nouryon, Akzo Nobel Functional Chemicals GmbH, Greiz, Germany.

Akzo Nobel Functional Chemicals GmbH
 Liebigstr.7, D-07973 Greiz, Germany
 Tel. +49-3661-78-0

thioplast@nouryon.com
<https://sulfurderivatives.nouryon.com/thioplast/>