

## Product Data Sheet

# Thioplast™ G21

Status:  
 December 2018

Liquid polysulfide polymer with thiol end groups

<b>Description</b>	Liquid Polysulfide Pre-polymer, end-capped by SH-functional end groups.																						
<b>Properties<sup>1)</sup></b> <small>1) Typical properties, not to be construed as product specifications</small>	<table> <tr> <td>Appearance</td> <td>brownish liquid polymer</td> </tr> <tr> <td>SH content</td> <td>2,5 – 3,1% (related to viscosity/Molecular weight)</td> </tr> <tr> <td>Viscosity (25 °C)</td> <td>10 – 20 Pas</td> </tr> <tr> <td>Av. Molecular weight</td> <td>2100 – 2700 g/mol (relative to SEC standard)</td> </tr> <tr> <td>Branching</td> <td>2,0 mol% (calculated on mol% TCP)</td> </tr> <tr> <td>Water content</td> <td>max. 0.35%</td> </tr> <tr> <td>Free sulfur</td> <td>0.01 – 0.1%</td> </tr> <tr> <td>Volatiles</td> <td>max. 0.5%</td> </tr> <tr> <td>Glass point</td> <td>approx. – 55 °C</td> </tr> <tr> <td>Flash point</td> <td>&gt; 230 °C</td> </tr> <tr> <td>CAS-No</td> <td>68611-50-7</td> </tr> </table>	Appearance	brownish liquid polymer	SH content	2,5 – 3,1% (related to viscosity/Molecular weight)	Viscosity (25 °C)	10 – 20 Pas	Av. Molecular weight	2100 – 2700 g/mol (relative to SEC standard)	Branching	2,0 mol% (calculated on mol% TCP)	Water content	max. 0.35%	Free sulfur	0.01 – 0.1%	Volatiles	max. 0.5%	Glass point	approx. – 55 °C	Flash point	> 230 °C	CAS-No	68611-50-7
Appearance	brownish liquid polymer																						
SH content	2,5 – 3,1% (related to viscosity/Molecular weight)																						
Viscosity (25 °C)	10 – 20 Pas																						
Av. Molecular weight	2100 – 2700 g/mol (relative to SEC standard)																						
Branching	2,0 mol% (calculated on mol% TCP)																						
Water content	max. 0.35%																						
Free sulfur	0.01 – 0.1%																						
Volatiles	max. 0.5%																						
Glass point	approx. – 55 °C																						
Flash point	> 230 °C																						
CAS-No	68611-50-7																						
<b>Application</b>	<p>Thioplast G21 is used to formulate flexible, highly elastic sealants being used in Insulating Glass applications with best performance in high Nobel Gas retention and low moisture vapor permeability.</p> <p>Furthermore, Thioplast G21 is used in low viscos sealants with good UV-resistance being used in construction applications.</p>																						
<b>Curing</b>	<p>Curing agent: Manganese(IV)-oxide (*): 7,5 – 9,4 g/100 g Thioplast G 21                  (*) Pure curing agent: Manganese (IV)-oxide. The concentration of active/activated Manganese (IV)-oxide needs to be considered.</p> <table> <tr> <td><b>Curing paste</b></td> <td><b>pbw</b></td> </tr> <tr> <td>MnO<sub>2</sub>, Grade Honeywell FA</td> <td>100</td> </tr> <tr> <td>Santicizer 278</td> <td>100</td> </tr> <tr> <td>Perkacit DPG</td> <td>6</td> </tr> <tr> <td>Airex 900</td> <td>7.4</td> </tr> </table> <p>Properties of Thioplast G21 cured with 21 g curing paste/100 g Thioplast G21:</p> <table> <tr> <td>Shore A-hardness</td> <td>min 38</td> </tr> <tr> <td>Elongation @ break %</td> <td>min 75</td> </tr> </table>	<b>Curing paste</b>	<b>pbw</b>	MnO <sub>2</sub> , Grade Honeywell FA	100	Santicizer 278	100	Perkacit DPG	6	Airex 900	7.4	Shore A-hardness	min 38	Elongation @ break %	min 75								
<b>Curing paste</b>	<b>pbw</b>																						
MnO <sub>2</sub> , Grade Honeywell FA	100																						
Santicizer 278	100																						
Perkacit DPG	6																						
Airex 900	7.4																						
Shore A-hardness	min 38																						
Elongation @ break %	min 75																						
<b>Packaging</b>	Thioplast G21 is available in 200 Liter drums, 1000 Liter IBC and 20m <sup>3</sup> ISO Bulk.																						
<b>Storage</b>	Store the container in cool and dry area, keep it closed when not in use. Shelf life under appropriate storage conditions min 3 years.																						
<b>Handling</b>	Full information on the safe handling is available in the Material Safety Data Sheet (MSDS). Further details are available upon request.																						

**Legal Disclaimer:** All information is based upon tests and data believed to be reliable, however, it is the user's responsibility to determine the suitability for his own use of the products described here. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent. All orders accepted shall be subjected to the standard conditions of sale of the manufacturing company, Nouryon, Akzo Nobel Functional Chemicals GmbH, Greiz, Germany.

Akzo Nobel Functional Chemicals GmbH  
 Liebigstr.7, D-07973 Greiz, Germany  
 Tel. +49-3661-78-0

[thioplast@nouryon.com](mailto:thioplast@nouryon.com)  
<https://sulfurderivatives.nouryon.com/thioplast/>