

Product Data Sheet

Thioplast™ G22

Status:
 December 2018

Liquid polysulfide polymer with thiol end groups

Description	Liquid Polysulfide Pre-polymer, end-capped by SH-functional end groups.																						
Properties¹⁾ <small>1) Typical properties, not to be construed as product specifications</small>	<table> <tr> <td>Appearance</td> <td>brownish liquid polymer</td> </tr> <tr> <td>SH content</td> <td>2,1 – 2,7% (related to viscosity/Molecular weight)</td> </tr> <tr> <td>Viscosity (25 °C)</td> <td>10 – 20 Pas</td> </tr> <tr> <td>Av. Molecular weight</td> <td>2400 – 3100 g/mol (relative to SEC standard)</td> </tr> <tr> <td>Branching</td> <td>0,5 mol% (calculated on mol% TCP)</td> </tr> <tr> <td>Water content</td> <td>max. 0.35%</td> </tr> <tr> <td>Free sulfur</td> <td>0.01 – 0.1%</td> </tr> <tr> <td>Volatiles</td> <td>max. 0.5%</td> </tr> <tr> <td>Glass point</td> <td>approx. – 55 °C</td> </tr> <tr> <td>Flash point</td> <td>> 230 °C</td> </tr> <tr> <td>CAS-No</td> <td>68611-50-7</td> </tr> </table>	Appearance	brownish liquid polymer	SH content	2,1 – 2,7% (related to viscosity/Molecular weight)	Viscosity (25 °C)	10 – 20 Pas	Av. Molecular weight	2400 – 3100 g/mol (relative to SEC standard)	Branching	0,5 mol% (calculated on mol% TCP)	Water content	max. 0.35%	Free sulfur	0.01 – 0.1%	Volatiles	max. 0.5%	Glass point	approx. – 55 °C	Flash point	> 230 °C	CAS-No	68611-50-7
Appearance	brownish liquid polymer																						
SH content	2,1 – 2,7% (related to viscosity/Molecular weight)																						
Viscosity (25 °C)	10 – 20 Pas																						
Av. Molecular weight	2400 – 3100 g/mol (relative to SEC standard)																						
Branching	0,5 mol% (calculated on mol% TCP)																						
Water content	max. 0.35%																						
Free sulfur	0.01 – 0.1%																						
Volatiles	max. 0.5%																						
Glass point	approx. – 55 °C																						
Flash point	> 230 °C																						
CAS-No	68611-50-7																						
Application	<p>Thioplast G22 is used to formulate flexible, highly elastic sealants being used in Insulating Glass- and Aerospace applications with best performance in Jet Fuel resistance, high Nobel Gas retention and low moisture vapor permeability.</p> <p>Furthermore, Thioplast G22 is used in highly elastic, low viscos sealants with good UV-resistance being used in construction applications.</p>																						
Curing	<p>Curing agent: Manganese(IV)-oxide (*): 7,5 – 9,4 g/100 g Thioplast G 22 (*) Pure curing agent: Manganese (IV)-oxide. The concentration of active/activated Manganese (IV)-oxide needs to be considered.</p> <table> <thead> <tr> <th>Curing paste</th> <th>pbw</th> </tr> </thead> <tbody> <tr> <td>MnO₂, Grade Honeywell FA</td> <td>100</td> </tr> <tr> <td>Santicizer 278</td> <td>100</td> </tr> <tr> <td>Perkacit DPG</td> <td>6</td> </tr> <tr> <td>Airex 900</td> <td>7.4</td> </tr> </tbody> </table> <p>Properties of Thioplast G22 cured with 20 g curing paste/100 g Thioplast G22:</p> <table> <tr> <td>Shore A-hardness</td> <td>min</td> <td>30</td> </tr> <tr> <td>Elongation @ break %</td> <td>min</td> <td>120</td> </tr> </table>	Curing paste	pbw	MnO ₂ , Grade Honeywell FA	100	Santicizer 278	100	Perkacit DPG	6	Airex 900	7.4	Shore A-hardness	min	30	Elongation @ break %	min	120						
Curing paste	pbw																						
MnO ₂ , Grade Honeywell FA	100																						
Santicizer 278	100																						
Perkacit DPG	6																						
Airex 900	7.4																						
Shore A-hardness	min	30																					
Elongation @ break %	min	120																					
Packaging	Thioplast G22 is available in 200 Liter drums, 1000 Liter IBC and 20m ³ ISO Bulk.																						
Storage	Store the container in cool and dry area, keep it closed when not in use. Shelf life under appropriate storage conditions min 3 years.																						
Handling	Full information on the safe handling is available in the Material Safety Data Sheet (MSDS). Further details are available upon request.																						

Legal Disclaimer: All information is based upon tests and data believed to be reliable, however, it is the user's responsibility to determine the suitability for his own use of the products described here. Nothing herein contained is to be construed as permission or as a recommendation to infringe any patent. All orders accepted shall be subjected to the standard conditions of sale of the manufacturing company, Nouryon, Akzo Nobel Functional Chemicals GmbH, Greiz, Germany.

Akzo Nobel Functional Chemicals GmbH
 Liebigstr.7, D-07973 Greiz, Germany
 Tel. +49-3661-78-0

thioplast@nouryon.com
<https://sulfurderivatives.nouryon.com/thioplast/>